


Fundo Solido

- Barrier-free shower element for PVC coverings
- Ideal substructure for high-pressure point loads
- Waterproof installation of the PVC to the drain



General product description

Floor-level shower element made of 100% recycled PET foam with a special mortar coating, especially developed for PVC coverings. Ideally suited for the applications listed below.

Areas of application

Shower places with soft, PVC flooring such as:

- hospitals
- private and public care facilities
- private bathrooms

Product properties

The Fundo Solido is a floor-level shower element for use beneath PVC floor coverings. It can withstand high-pressure point loads, e.g. wheelchairs or walking aids.

With the help of the wedi Fundo extension panels, the entire floor in the wet room can be realised in the wedi system – but the substrate must be able to support the loads that occur.

Sub-surface requirements, processing

Information on processing can be found in the installation instruction (see www.wedi.net).



Technical properties of raw foam

Material list	PET foam
Maximum pressure stress (ISO 844)	4 N/mm ²
Thermal conductivity EN 13164	0,043 W/mK
Raw density (ISO 845)	200 kg/m ³
Temperature limits	-20°C / +150°C
Fire behavior EN 13501-1	E
Outgassing	none

Technical properties of Fundo Solido

Thickness	40 mm
Wheelchair-accessible	Yes
Height of the Fundo Solido DN50 Horizontal drain	84 mm
Height of the Fundo Solido DN50 Vertical drain	144 mm
Surface gradients	See the technical drawing
Stainless steel grid	Ø 115 mm

Delivery form

1 box

Storage

The Fundo Solido should always be stored on its side, and must be protected from direct sunlight and moisture.

Safety notice

none

Information about finishing and application options for wedi products, technical recommendations or advice and other information provided by our employees (technical usage advice) is accurate to the best of our knowledge, but is non-binding and is given with the exclusion of any liability. It does not exempt our customers and their buyers from carrying out their own checks and trials on the suitability of the products for the intended processes and purposes.